

Intertek ETL Semko
IMO Res. A. 652(16)
Test Results
(This is not a report)

Client: American Leather

Project No: 3146324SAT-001

Date: 3/5/08

Specimen Identification: IMO #1

TEST DATA

Smouldering Cigarette

CRITERIA		Test 1	Test 2
Progressive Smouldering*	(Y/N)	No	No
Flaming*	(Y/N)	No	No
Progressive smouldering on final examination	(Y/N)	No	No

**Within the test duration (1 hour from the beginning of the test)*

Smouldering Cigarette Test Notes

Test #1: All smoldering ceased at 34:15.

Test #2: All smoldering ceased at 33:25.

Butane Flame Test

CRITERIA		Test 1	Test 2
Flaming after 120 seconds*	(Y/N)	No	No
Progressive Smouldering after 120 seconds*	(Y/N)	No	No
Progressive smouldering on final examination	(Y/N)	No	No

**120 seconds after removal of the burner tube*

Butane Flame Test Notes

Test #1: Flames out 2 seconds after removal of the burner tube.

Test #2: Flames out 2 seconds after removal of the burner tube.

THE SPECIMEN PASSED THE TEST CRITERIA